# ASA-UV-BK-175 ? Technical Datasheet

## ASA UV-Resistant ? Black

---

Type: ASA

Diameter: 1.75mm

Density: 1.07 g/cm‡

Melting / print temp: 250-270℃

Nozzle temp: 250-270℃

Bed temp: 90-110℃

Tensile strength: 42-52 MPa

Elongation at break: 15-30 %

Hardness: Shore D 78

Spool weight: 1.0 kg

Certifications: ISO 9001, RoHS, UV Stabilised

---

DEMO DOCUMENT ? replace with your own datasheet before launch.